

ADDENDUM
to the 2018 Edition of the
Design Values for Wood Construction
(a supplement to the *National Design Specification® (NDS®) for Wood Construction*)
(All print and electronic versions)

<u>Page</u>	<u>Revision</u>
62	Add new Table 4G, Reference Design Values for Multi-Species and Country Graded Visually Graded Dimension Lumber (2"–4" thick) as shown on the following pages.

Table 4; Adjustment Factors

Repetitive Member Factor, C_r

Bending design values, F_b , for dimension lumber 2" to 4" thick shall be multiplied by the repetitive member factor, $C_r = 1.15$, when such members are used as joists, truss chords, rafters, studs, planks, decking, or similar members which are in contact or spaced not more than 24" on center, are not less than 3 in number and are joined by floor, roof, or other load distributing elements adequate to support the design load.

Wet Service Factor, C_M

When dimension lumber is used where moisture content will exceed 19% for an extended time period, design values shall be multiplied by the appropriate wet service factors from the following table:

Wet Service Factors, C_M

F_b	F_t	F_v	$F_{c\perp}$	F_c	E and E_{min}
0.85*	1.0	0.97	0.67	0.8**	0.9

* when $(F_b)(C_F) \leq 1,150$ psi, $C_M = 1.0$

** when $(F_c)(C_F) \leq 750$ psi, $C_M = 1.0$

Flat Use Factor, C_{fu}

Bending design values adjusted by size factors are based on edgewise use (load applied to narrow face). When dimension lumber is used flatwise (load applied to wide face), the bending design value, F_b , shall also be permitted to be multiplied by the following flat use factors:

Flat Use Factors, C_{fu}

Width (depth)	Thickness (breadth)	
	2" & 3"	4"
2" & 3"	1.0	—
4"	1.1	1.0
5"	1.1	1.05
6"	1.15	1.05
8"	1.15	1.05
10" & wider	1.2	1.1

NOTE

To facilitate the use of Table 4I, shading has been employed to distinguish design values based on a 4" nominal width (Construction, Standard, and Utility grades) or a 6" nominal width (Stud grade) from design values based on a 12" nominal width (Select Structural, No.1 & Btr, No.1, No.2, and No.3 grades).

Size Factor, C_F

Tabulated bending, tension, and compression parallel to grain design values for dimension lumber 2" to 4" thick shall be multiplied by the following size factors:

Size Factors, C_F

Grades	Width (depth)	F_b		F_t	F_c
		Thickness (breadth)			
		2" & 3"	4"		
Select Structural, No.1 & Btr, No.1, No.2, No.3	2", 3", & 4"	1.5	1.5	1.5	1.15
	5"	1.4	1.4	1.4	1.1
	6"	1.3	1.3	1.3	1.1
	8"	1.2	1.3	1.2	1.05
	10"	1.1	1.2	1.1	1.0
	12"	1.0	1.1	1.0	1.0
	14" & wider	0.9	1.0	0.9	0.9
Stud	2", 3", & 4"	1.1	1.1	1.1	1.05
	5" & 6"	1.0	1.0	1.0	1.0
	8" & wider	Use No.3 Grade tabulated design values and size factors			
Construction, Standard	2", 3", & 4"	1.0	1.0	1.0	1.0
Utility	4"	1.0	1.0	1.0	1.0
	2" & 3"	0.4	—	0.4	0.6

Table 4G

Reference Design Values for Multi-Species and Country Graded Visually Graded Dimension Lumber (2" - 4" thick)^{1,2,3}

(Tabulated design values are for normal load duration and dry service conditions. See NDS 4.3 for a comprehensive description of design value adjustment factors.)

USE WITH TABLE 4G ADJUSTMENT FACTORS

Multi-Species and Country Label	Commercial Grade	Size Classification	Design values in pounds per square inch (psi)							Specific Gravity ⁴ G	Grade Stamping Agency
			Bending	Tension parallel to grain	Shear parallel to grain	Compression perpendicular to grain	Compression parallel to grain	Modulus of Elasticity			
			F _b	F _t	F _v	F _{c⊥}	F _c	E	E _{min}		
As-N Spr-Sc P (I) AUS ROM UKR											
AUSTRIAN SPRUCE from AUSTRIA, NORWAY SPRUCE & SCOTS PINE from AUSTRIA, ROMANIA, & UKRAINE											
<p>Tabulated design values are the minimum values for the following species and commercial grades in Table 4F: AUSTRIAN SPRUCE from AUSTRIA & THE CZECH REPUBLIC; NORWAY SPRUCE from ROMANIA & UKRAINE; SCOTS PINE from AUSTRIA & THE CZECH REPUBLIC, ROMANIA, & UKRAINE</p>	Select Structural	2" & wider	1250	575	100	260	1200	1.5	0.55	0.38	PLIB
	No. 1		850	375	100	260	1050	1.4	0.51		
	No. 2		725	325	100	260	950	1.2	0.44		
	No. 3	425	200	100	260	550	1.1	0.40			
	Stud	2" & wider	575	250	100	260	600	1.1	0.40		
	Construction	2" - 4" wide	850	375	100	260	1200	1.1	0.40		
	Standard		475	200	100	260	1000	1	0.37		
Utility	225		100	100	260	650	1	0.37			
AS-Sc P (I) AUS											
AUSTRIAN SPRUCE & SCOTS PINE from AUSTRIA											
<p>Tabulated design values are the minimum values for the following species and commercial grades in Table 4F: AUSTRIAN SPRUCE from AUSTRIA & THE CZECH REPUBLIC; SCOTS PINE from AUSTRIA & THE CZECH REPUBLIC, ROMANIA, & UKRAINE</p>	Select Structural	2" & wider	1300	600	135	260	1200	1.7	0.62	0.43	PLIB
	No. 1		900	400	135	260	1050	1.6	0.58		
	No. 2		775	350	135	260	1000	1.4	0.51		
	No. 3	450	200	135	260	575	1.3	0.47			
	Stud	2" & wider	600	275	135	260	625	1.3	0.47		
	Construction	2" - 4" wide	875	400	135	260	1200	1.3	0.47		
	Standard		500	225	135	260	1000	1.2	0.44		
Utility	225		100	135	260	675	1.1	0.40			
AS/NSPR/SCOTP(I)AUS/GER											
AUSTRIAN SPRUCE from AUSTRIA, NORWAY SPRUCE & SCOTS PINE from AUSTRIA & GERMANY ⁵											
<p>Tabulated design values are the minimum values for the following species and commercial grades in Table 4F: AUSTRIAN SPRUCE from AUSTRIA & THE CZECH REPUBLIC; NORWAY SPRUCE from GERMANY, NE FRANCE, & SWITZERLAND; SCOTS PINE from AUSTRIA & THE CZECH REPUBLIC, ROMANIA, & UKRAINE; SCOTS PINE from GERMANY⁵</p>	Select Structural	2" & wider	1200	550	135	260	1200	1.6	0.58	0.42	TP
	No. 1		800	375	135	260	1050	1.4	0.51		
	No. 2		700	325	135	260	950	1.1	0.40		
	No. 3	400	175	135	260	550	1	0.37			
	Stud	2" & wider	550	250	135	260	600	1	0.37		
	Construction	2" - 4" wide	800	375	135	260	1150	1.1	0.40		
	Standard		450	200	135	260	975	1	0.37		
Utility	225		100	135	260	625	0.9	0.33			

Table 4G

Reference Design Values for Multi-Species and Country Grademarked Visually Graded Dimension Lumber (2" - 4" thick)^{1,2,3}

(Tabulated design values are for normal load duration and dry service conditions. See NDS 4.3 for a comprehensive description of design value adjustment factors.)

USE WITH TABLE 4G ADJUSTMENT FACTORS

Multi-Species and Country Label	Commercial Grade	Size Classification	Design values in pounds per square inch (psi)							Specific Gravity ⁴ G	Grade Stamping Agency
			Bending	Tension parallel to grain	Shear parallel to grain	Compression perpendicular to grain	Compression parallel to grain	Modulus of Elasticity			
			F _b	F _t	F _v	F _{c⊥}	F _c	E	E _{min}		
DF/DF-N	DOUGLAS FIR & DOUGLAS FIR (NORTH)									TP	
DF-L/DF-L(N)	DOUGLAS FIR-LARCH & DOUGLAS FIR-LARCH (NORTH)									PLIB, WWPA	
DF-L/DF(N)	DOUGLAS FIR-LARCH & DOUGLAS FIR (NORTH)									PLIB	
<p>Tabulated design values are the minimum values for the following species and commercial grades in Table 4A: DOUGLAS FIR-LARCH & DOUGLAS FIR-LARCH (NORTH)</p>	Select Structural	2" & wider	1350	825	180	625	1700	1.9	0.69	0.49	
	No. 1 & Btr		1150	750	180	625	1550	1.8	0.66		
	No. 1		850	500	180	625	1400	1.6	0.58		
	No. 2	850	500	180	625	1350	1.6	0.58			
	No. 3	475	300	180	625	775	1.4	0.51			
	Stud	2" & wider	650	400	180	625	850	1.4	0.51		
	Construction	2" - 4" wide	950	575	180	625	1650	1.5	0.55		
Standard	525		325	180	625	1400	1.4	0.51			
Utility	250		150	180	625	900	1.3	0.47			
D Fir-L-HF	DOUGLAS FIR-LARCH & HEM-FIR from U.S.									PLIB	
DF-HF	DOUGLAS FIR & HEM-FIR from U.S.										
<p>Tabulated design values are the minimum values for the following species and commercial grades in Table 4A: DOUGLAS FIR-LARCH; HEM-FIR</p>	Select Structural	2" & wider	1400	925	150	405	1500	1.6	0.58	0.43	
	No. 1&Btr		1100	725	150	405	1350	1.5	0.55		
	No. 1		975	625	150	405	1350	1.5	0.55		
	No. 2	850	525	150	405	1300	1.3	0.47			
	No. 3	500	300	150	405	725	1.2	0.44			
	Stud	2" & wider	675	400	150	405	800	1.2	0.44		
	Construction	2" - 4" wide	975	600	150	405	1550	1.3	0.47		
Standard	550		325	150	405	1300	1.2	0.44			
Utility	250		150	150	405	850	1.1	0.40			
DF-HF-SPF	DOUGLAS FIR, HEM-FIR & SPRUCE-PINE-FIR from NORTH AMERICA									PLIB	
<p>Tabulated design values are the minimum values for the following species and commercial grades in Table 4A: DOUGLAS FIR-LARCH; HEM-FIR; SPRUCE-PINE-FIR</p>	Select Structural	2" & wider	1250	700	135	405	1400	1.5	0.55	0.42	
	No. 1		875	450	135	405	1150	1.4	0.51		
	No. 2		850	450	135	405	1150	1.3	0.47		
	No. 3	500	250	135	405	650	1.2	0.44			
	Stud	2" & wider	675	350	135	405	725	1.2	0.44		
	Construction	2" - 4" wide	975	500	135	405	1400	1.3	0.47		
	Standard		550	275	135	405	1150	1.2	0.44		
Utility	250		125	135	405	750	1.1	0.40			

Table 4G

Reference Design Values for Multi-Species and Country Graded Visually Graded Dimension Lumber (2" - 4" thick)^{1,2,3}

(Tabulated design values are for normal load duration and dry service conditions. See NDS 4.3 for a comprehensive description of design value adjustment factors.)

USE WITH TABLE 4G ADJUSTMENT FACTORS

Multi-Species and Country Label	Commercial Grade	Size Classification	Design values in pounds per square inch (psi)							Specific Gravity ⁴ G	Grade Stamping Agency
			Bending	Tension parallel to grain	Shear parallel to grain	Compression perpendicular to grain	Compression parallel to grain	Modulus of Elasticity			
			F _b	F _t	F _v	F _{c⊥}	F _c	E	E _{min}		
DF-HF-SPF(S) DOUGLAS FIR, HEM-FIR & SPRUCE-PINE-FIR (SOUTH) from U.S.											
Tabulated design values are the minimum values for the following species and commercial grades in Table 4A: DOUGLAS FIR-LARCH; HEM-FIR; SPRUCE-PINE-FIR (SOUTH)	Select Structural	2" & wider	1300	575	135	335	1200	1.3	0.47	0.36	PLIB
	No. 1		875	400	135	335	1050	1.2	0.44		
	No. 2		775	350	135	335	1000	1.1	0.40		
	No. 3	450	200	135	335	575	1	0.37			
	Stud	2" & wider	600	275	135	335	625	1	0.37		
	Construction	2" - 4" wide	875	400	135	335	1200	1	0.37		
	Standard		500	225	135	335	1000	0.9	0.33		
Utility		225	100	135	335	675	0.9	0.33			
D Fir-SPF DOUGLAS FIR & SPRUCE-PINE-FIR from NORTH AMERICA											
DF-L-SPF DOUGLAS FIR-LARCH & SPRUCE-PINE-FIR from NORTH AMERICA											
Tabulated design values are the minimum values for the following species and commercial grades in Table 4A: DOUGLAS FIR-LARCH; SPRUCE-PINE-FIR	Select Structural	2" & wider	1250	700	135	425	1400	1.5	0.55	0.42	PLIB
	No. 1		875	450	135	425	1150	1.4	0.51		
	No. 2		875	450	135	425	1150	1.4	0.51		
	No. 3	500	250	135	425	650	1.2	0.44			
	Stud	2" & wider	675	350	135	425	725	1.2	0.44		
	Construction	2" - 4" wide	1000	500	135	425	1400	1.3	0.47		
	Standard		550	275	135	425	1150	1.2	0.44		
Utility		275	125	135	425	750	1.1	0.40			
DF-N Spr (I) N FRA DOUGLAS FIR & NORWAY SPRUCE from NORTHERN FRANCE											
Tabulated design values are the minimum values for the following species and commercial grades in Table 4F: DOUGLAS FIR from FRANCE & GERMANY; NORWAY SPRUCE from GERMANY, NE FRANCE, & SWITZERLAND	Select Structural	2" & wider	1200	550	170	355	1200	1.6	0.58	0.42	PLIB
	No. 1		825	375	170	355	1050	1.4	0.51		
	No. 2		725	325	170	355	950	1.2	0.44		
	No. 3	425	200	170	355	550	1.1	0.40			
	Stud	2" & wider	575	250	170	355	600	1.1	0.40		
	Construction	2" - 4" wide	825	375	170	355	1200	1.1	0.40		
	Standard		475	200	170	355	975	1	0.37		
Utility		225	100	170	355	650	0.9	0.33			
DF/NSPR/SCOTP(I)GER/ROM/SW/UKR DOUGLAS FIR from GERMANY, NORWAY SPRUCE & SCOTS PINE from GERMANY ⁵ , ROMANIA, SWEDEN, or UKRAINE											
Tabulated design values are the minimum values for the following species and commercial grades in Table 4F: DOUGLAS FIR from FRANCE & GERMANY; NORWAY SPRUCE from GERMANY, NE FRANCE, & SWITZERLAND; NORWAY SPRUCE from ROMANIA & UKRAINE; NORWAY SPRUCE from SWEDEN; SCOTS PINE from AUSTRIA & THE CZECH REPUBLIC, ROMANIA, & UKRAINE; SCOTS_PINE from GERMANY ⁵ ; SCOTS PINE from SWEDEN	Select Structural	2" & wider	1200	550	100	270	1200	1.5	0.55	0.38	TP
	No. 1		800	375	100	270	1000	1.4	0.51		
	No. 2		575	250	100	270	825	1.1	0.40		
	No. 3	325	150	100	270	475	1	0.37			
	Stud	2" & wider	450	200	100	270	525	1	0.37		
	Construction	2" - 4" wide	650	300	100	270	1050	1.1	0.40		
	Standard		375	175	100	270	850	1	0.37		
Utility		175	75	100	270	550	0.9	0.33			

Table 4G

Reference Design Values for Multi-Species and Country Graded Visually Graded Dimension Lumber (2" - 4" thick)^{1,2,3}

(Tabulated design values are for normal load duration and dry service conditions. See NDS 4.3 for a comprehensive description of design value adjustment factors.)

USE WITH TABLE 4G ADJUSTMENT FACTORS

Multi-Species and Country Label	Commercial Grade	Size Classification	Design values in pounds per square inch (psi)							Specific Gravity ⁴ G	Grade Stamping Agency
			Bending	Tension parallel to grain	Shear parallel to grain	Compression perpendicular to grain	Compression parallel to grain	Modulus of Elasticity			
			F _b	F _t	F _v	F _{c⊥}	F _c	E	E _{min}		
DF/NSPR/SCOTP(I)GER											
			DOUGLAS FIR, NORWAY SPRUCE, & SCOTS PINE from GERMANY⁵								
Tabulated design values are the minimum values for the following species and commercial grades in Table 4F: DOUGLAS FIR from FRANCE & GERMANY; NORWAY SPRUCE from GERMANY, NE FRANCE, & SWITZERLAND; SCOTS PINE from GERMANY ⁵	Select Structural	2" & wider	1200	550	160	355	1200	1.6	0.58	0.42	TP
	No. 1		800	375	160	355	1050	1.4	0.51		
	No. 2		700	325	160	355	950	1.1	0.40		
	No. 3	400	175	160	355	550	1	0.37			
	Stud	2" & wider	550	250	160	355	600	1	0.37		
	Construction	2" - 4" wide	800	375	160	355	1150	1.1	0.40		
	Standard		450	200	160	355	975	1	0.37		
Utility	225		100	160	355	625	0.9	0.33			
ES-LP											
			ENGELMANN SPRUCE & LODGEPOLE PINE from NORTH AMERICA								
Tabulated design values are the minimum values for the following species and commercial grades in Table 4A: SPRUCE-PINE-FIR (SOUTH)	Select Structural	2" & wider	1300	575	135	335	1200	1.3	0.47	0.36	PLIB, WWPA
	No. 1		875	400	135	335	1050	1.2	0.44		
	No. 2		775	350	135	335	1000	1.1	0.40		
	No. 3	450	200	135	335	575	1	0.37			
	Stud	2" & wider	600	275	135	335	625	1	0.37		
	Construction	2" - 4" wide	875	400	135	335	1200	1	0.37		
	Standard		500	225	135	335	1000	0.9	0.33		
Utility	225		100	135	335	675	0.9	0.33			
ES-LP-AF											
			ENGELMANN SPRUCE, LODGEPOLE PINE & SUBALPINE FIR from U.S.								
Tabulated design values are the minimum values for the following species and commercial grades in Table 4A: SPRUCE-PINE-FIR (SOUTH); WESTERN WOODS	Select Structural	2" & wider	900	400	135	335	1050	1.2	0.44	0.36	PLIB, WWPA
	No. 1		675	300	135	335	950	1.1	0.37		
	No. 2		675	300	135	335	900	1	0.37		
	No. 3	375	175	135	335	525	0.9	0.33			
	Stud	2" & wider	525	225	135	335	575	0.9	0.33		
	Construction	2" - 4" wide	775	350	135	335	1100	1	0.33		
	Standard		425	200	135	335	925	0.9	0.29		
Utility	200		100	135	335	600	0.8	0.29			
HF/DF-N/SPF/SPF-S											
			HEM-FIR, DOUGLAS FIR (NORTH), SPRUCE-PINE-FIR & SPRUCE-PINE-FIR (SOUTH) from NORTH AMERICA								
Tabulated design values are the minimum values for the following species and commercial grades in Table 4A: HEM-FIR; DOUGLAS FIR-LARCH (NORTH); SPRUCE-PINE-FIR; SPRUCE-PINE-FIR (SOUTH)	Select Structural	2" & wider	1250	575	135	335	1200	1.3	0.47	0.36	TP
	No. 1		850	400	135	335	1050	1.2	0.44		
	No. 2		775	350	135	335	1000	1.1	0.40		
	No. 3	450	200	135	335	575	1	0.37			
	Stud	2" & wider	600	275	135	335	625	1	0.37		
	Construction	2" - 4" wide	875	400	135	335	1200	1	0.37		
	Standard		500	225	135	335	1000	0.9	0.33		
Utility	225		100	135	335	675	0.9	0.33			

Table 4G

Reference Design Values for Multi-Species and Country Graded Visually Graded Dimension Lumber (2" - 4" thick)^{1,2,3}

(Tabulated design values are for normal load duration and dry service conditions. See NDS 4.3 for a comprehensive description of design value adjustment factors.)

USE WITH TABLE 4G ADJUSTMENT FACTORS

Multi-Species and Country Label	Commercial Grade	Size Classification	Design values in pounds per square inch (psi)							Specific Gravity ⁴ G	Grade Stamping Agency
			Bending	Tension parallel to grain	Shear parallel to grain	Compression perpendicular to grain	Compression parallel to grain	Modulus of Elasticity			
			F _b	F _t	F _v	F _{c⊥}	F _c	E	E _{min}		
HF/HF(N)			HEM-FIR & HEM-FIR (NORTH) from NORTH AMERICA								PLIB, WWPA
HF/HF-N			HEM-FIR & HEM-FIR (NORTH) from NORTH AMERICA								TP
Tabulated design values are the minimum values for the following species and commercial grades in Table 4A: HEM-FIR; HEM-FIR (NORTH)	Select Structural		1300	775	145	405	1500	1.6	0.58	0.43	
	No. 1 & Btr		1100	725	145	405	1350	1.5	0.55		
	No. 1	2" & wider	975	575	145	405	1350	1.5	0.55		
	No. 2		850	525	145	405	1300	1.3	0.47		
	No. 3		500	300	145	405	725	1.2	0.44		
	Stud	2" & wider	675	400	145	405	800	1.2	0.44		
	Construction Standard	2" - 4" wide	975	600	145	405	1550	1.3	0.47		
Utility		550	325	145	405	1300	1.2	0.44			
			250	150	145	405	850	1.1	0.40		
HF-SS			HEM-FIR & SITKA SPRUCE from U.S.								PLIB
Tabulated design values are the minimum values for the following species and commercial grades in Table 4A: HEM-FIR; SPRUCE-PINE-FIR (SOUTH)	Select Structural		1300	575	135	335	1200	1.3	0.47	0.36	
	No. 1		875	400	135	335	1050	1.2	0.44		
	No. 2	2" & wider	775	350	135	335	1000	1.1	0.40		
	No. 3		450	200	135	335	575	1	0.37		
	Stud	2" & wider	600	275	135	335	625	1	0.37		
	Construction Standard	2" - 4" wide	875	400	135	335	1200	1	0.37		
	Utility		500	225	135	335	1000	0.9	0.33		
			225	100	135	335	675	0.9	0.33		
N Spr (I) EST FIN GER LTH NOR SW			NORWAY SPRUCE from ESTONIA, FINLAND, GERMANY, LITHUANIA, NORWAY, & SWEDEN								PLIB
Tabulated design values are the minimum values for the following species and commercial grades in Table 4F: NORWAY SPRUCE from ESTONIA, LATVIA, & LITHUANIA; NORWAY SPRUCE from FINLAND; NORWAY SPRUCE from GERMANY, NE FRANCE, & SWITZERLAND; NORWAY SPRUCE from NORWAY; NORWAY SPRUCE from SWEDEN	Select Structural		1200	550	115	220	1200	1.5	0.55	0.42	
	No. 1		825	375	115	220	1000	1.4	0.51		
	No. 2	2" & wider	625	275	115	220	875	1.2	0.44		
	No. 3		375	175	115	220	500	1.1	0.40		
	Stud	2" & wider	550	250	115	220	575	1.1	0.40		
	Construction Standard	2" - 4" wide	725	325	115	220	1100	1.1	0.40		
	Utility		400	175	115	220	900	1	0.37		
			200	75	115	220	600	0.9	0.33		

Table 4G

Reference Design Values for Multi-Species and Country Graded Visually Graded Dimension Lumber (2" - 4" thick)^{1,2,3}

(Tabulated design values are for normal load duration and dry service conditions. See NDS 4.3 for a comprehensive description of design value adjustment factors.)

USE WITH TABLE 4G ADJUSTMENT FACTORS

Multi-Species and Country Label	Commercial Grade	Size Classification	Design values in pounds per square inch (psi)							Specific Gravity ⁴ G	Grade Stamping Agency
			Bending	Tension parallel to grain	Shear parallel to grain	Compression perpendicular to grain	Compression parallel to grain	Modulus of Elasticity			
			F _b	F _t	F _v	F _{c⊥}	F _c	E	E _{min}		
N Spr-Sc P() EST			NORWAY SPRUCE & SCOTS PINE from ESTONIA								PLIB
N Spr-Sc P() LAT			NORWAY SPRUCE & SCOTS PINE from LATVIA								PLIB
N Spr-Sc P() LTH			NORWAY SPRUCE & SCOTS PINE from LITHUANIA								PLIB
NSPR/SCOTP()LAT/LTH			NORWAY SPRUCE & SCOTS PINE from LATVIA & LITHUANIA								TP
Tabulated design values are the minimum values for the following species and commercial grades in Table 4F: NORWAY SPRUCE from ESTONIA, LATVIA, & LITHUANIA; SCOTS PINE from ESTONIA, LATVIA, & LITHUANIA	Select Structural	2" & wider	1150	525	130	430	1150	1.5	0.55	0.42	
	No. 1		800	350	130	430	1050	1.4	0.51		
	No. 2		750	325	130	430	975	1.2	0.44		
	No. 3	425	200	130	430	550	1.1	0.40			
	Stud	2" & wider	575	275	130	430	625	1.1	0.40		
	Construction	2" - 4" wide	850	375	130	430	1200	1.1	0.40		
	Standard		475	225	130	430	1000	1	0.37		
Utility	225		100	130	430	650	1	0.37			
N Spr-Sc P() FIN			NORWAY SPRUCE & SCOTS PINE from FINLAND								PLIB
Tabulated design values are the minimum values for the following species and commercial grades in Table 4F: NORWAY SPRUCE from FINLAND; SCOTS PINE from FINLAND	Select Structural	2" & wider	1300	600	125	210	1200	1.5	0.55	0.42	
	No. 1		825	375	125	210	1000	1.4	0.51		
	No. 2		625	275	125	210	875	1.2	0.44		
	No. 3	375	175	125	210	500	1.1	0.40			
	Stud	2" & wider	575	250	125	210	600	1.1	0.40		
	Construction	2" - 4" wide	725	325	125	210	1100	1.1	0.40		
	Standard		400	175	125	210	900	1	0.37		
Utility	200		75	125	210	600	1	0.37			
N Spr-Sc P() GER			NORWAY SPRUCE & SCOTS PINE from GERMANY ⁵								PLIB
Tabulated design values are the minimum values for the following species and commercial grades in Table 4F: NORWAY SPRUCE from GERMANY, NE FRANCE, & SWITZERLAND; SCOTS PINE from GERMANY ⁵	Select Structural	2" & wider	1200	550	160	355	1200	1.6	0.58	0.42	
	No. 1		800	375	160	355	1050	1.4	0.51		
	No. 2		700	325	160	355	950	1.1	0.40		
	No. 3	400	175	160	355	550	1	0.37			
	Stud	2" & wider	550	250	160	355	600	1	0.37		
	Construction	2" - 4" wide	800	375	160	355	1150	1.1	0.40		
	Standard		450	200	160	355	975	1	0.37		
Utility	225		100	160	355	625	0.9	0.33			

Table 4G

Reference Design Values for Multi-Species and Country Grademarked Visually Graded Dimension Lumber (2" - 4" thick)^{1,2,3}

(Tabulated design values are for normal load duration and dry service conditions. See NDS 4.3 for a comprehensive description of design value adjustment factors.)

USE WITH TABLE 4G ADJUSTMENT FACTORS

Multi-Species and Country Label	Commercial Grade	Size Classification	Design values in pounds per square inch (psi)							Specific Gravity ⁴ G	Grade Stamping Agency
			Bending	Tension parallel to grain	Shear parallel to grain	Compression perpendicular to grain	Compression parallel to grain	Modulus of Elasticity			
			F _b	F _t	F _v	F _{c⊥}	F _c	E	E _{min}		
N Spr-Sc P() ROM	NORWAY SPRUCE & SCOTS PINE from ROMANIA										
N Spr-Sc P() ROM-UKR	NORWAY SPRUCE & SCOTS PINE from ROMANIA & UKRAINE										
Tabulated design values are the minimum values for the following species and commercial grades in Table 4F: NORWAY SPRUCE from ROMANIA & UKRAINE; SCOTS PINE from AUSTRIA & THE CZECH REPUBLIC, ROMANIA, & UKRAINE	Select Structural	2" & wider	1250	575	100	270	1200	1.5	0.55	0.38	
	No. 1		850	375	100	270	1050	1.4	0.51		
	No. 2		725	325	100	270	950	1.2	0.44		
	No. 3	425	200	100	270	550	1.1	0.40			
	Stud	2" & wider	575	250	100	270	600	1.1	0.40		
	Construction	2" - 4" wide	850	375	100	270	1200	1.1	0.40		
	Standard		475	200	100	270	1000	1	0.37		
Utility	225		100	100	270	650	1	0.37			
N Spr-Sc P() SW	NORWAY SPRUCE & SCOTS PINE from SWEDEN										
Tabulated design values are the minimum values for the following species and commercial grades in Table 4F: NORWAY SPRUCE from SWEDEN; SCOTS PINE from SWEDEN	Select Structural	2" & wider	1250	550	120	285	1200	1.6	0.58	0.42	
	No. 1		825	375	120	285	1000	1.4	0.51		
	No. 2		575	250	120	285	825	1.2	0.44		
	No. 3	325	150	120	285	475	1.1	0.40			
	Stud	2" & wider	450	200	120	285	525	1.1	0.40		
	Construction	2" - 4" wide	650	300	120	285	1050	1.2	0.44		
	Standard		375	175	120	285	850	1.1	0.40		
Utility	175		75	120	285	550	1	0.37			
N Spr-S Fir () GER	NORWAY SPRUCE & SILVER FIR from GERMANY										
N Spr-S Fir () N FRA	NORWAY SPRUCE & SILVER FIR from NORTHERN FRANCE										
N Spr-S Fir() GER N FRA	NORWAY SPRUCE & SILVER FIR from GERMANY & NORTHERN FRANCE										
Tabulated design values are the minimum values for the following species and commercial grades in Table 4F: NORWAY SPRUCE from GERMANY, NE FRANCE, & SWITZERLAND; SILVER FIR (<i>Abies alba</i>) from GERMANY, NE FRANCE, & SWITZERLAND	Select Structural	2" & wider	950	425	125	355	1100	1.5	0.55	0.42	
	No. 1		725	325	125	355	975	1.4	0.51		
	No. 2		725	325	125	355	950	1.2	0.44		
	No. 3	425	200	125	355	550	1.1	0.40			
	Stud	2" & wider	575	250	125	355	600	1.1	0.40		
	Construction	2" - 4" wide	825	375	125	355	1150	1.1	0.40		
	Standard		475	200	125	355	975	1	0.37		
Utility	225		100	125	355	650	0.9	0.33			

Table 4G

Reference Design Values for Multi-Species and Country Graded Visually Graded Dimension Lumber (2" - 4" thick)^{1,2,3}

(Tabulated design values are for normal load duration and dry service conditions. See NDS 4.3 for a comprehensive description of design value adjustment factors.)

USE WITH TABLE 4G ADJUSTMENT FACTORS

Multi-Species and Country Label	Commercial Grade	Size Classification	Design values in pounds per square inch (psi)							Specific Gravity ⁴ G	Grade Stamping Agency
			Bending	Tension parallel to grain	Shear parallel to grain	Compression perpendicular to grain	Compression parallel to grain	Modulus of Elasticity			
			F _b	F _t	F _v	F _{c⊥}	F _c	E	E _{min}		
N Spr-Sc P-DF (I) GER											
NORWAY SPRUCE, SCOTS PINE & DOUGLAS FIR from GERMANY ⁵											
Tabulated design values are the minimum values for the following species and commercial grades in Table 4F: NORWAY SPRUCE from GERMANY, NE FRANCE, & SWITZERLAND; SCOTS PINE from GERMANY ⁵ ; DOUGLAS FIR from FRANCE & GERMANY	Select Structural	2" & wider	1200	550	160	355	1200	1.6	0.58	0.42	PLIB
	No. 1		800	375	160	355	1050	1.4	0.51		
	No. 2		700	325	160	355	950	1.1	0.40		
	No. 3	400	175	160	355	550	1	0.37			
	Stud	2" & wider	550	250	160	355	600	1	0.37		
	Construction	2" - 4" wide	800	375	160	355	1150	1.1	0.40		
	Standard		450	200	160	355	975	1	0.37		
	Utility		225	100	160	355	625	0.9	0.33		
N Spr-Sc P-DF-L (I) GER											
NORWAY SPRUCE, & SCOTS PINE from GERMANY ⁵ , & DOUGLAS FIR/EUROPEAN LARCH from AUSTRIA, THE CZECH REPUBLIC & BAVARIA ⁶											
Tabulated design values are the minimum values for the following species and commercial grades in Table 4F: NORWAY SPRUCE from GERMANY, NE FRANCE, & SWITZERLAND; SCOTS PINE from GERMANY ⁵ ; DOUGLAS FIR/EUROPEAN LARCH from AUSTRIA, THE CZECH REPUBLIC & BAVARIA ⁶	Select Structural	2" & wider	1200	550	160	355	1200	1.6	0.58	0.42	PLIB
	No. 1		800	375	160	355	1050	1.4	0.51		
	No. 2		700	325	160	355	950	1.1	0.40		
	No. 3	400	175	160	355	550	1	0.37			
	Stud	2" & wider	550	250	160	355	600	1	0.37		
	Construction	2" - 4" wide	800	375	160	355	1150	1.1	0.40		
	Standard		450	200	160	355	975	1	0.37		
	Utility		225	100	160	355	625	0.9	0.33		
N Spr-Sc P-DF-S Fir (I) GER											
NORWAY SPRUCE, SCOTS PINE, & SILVER FIR from GERMANY ⁵ , & DOUGLAS FIR/EUROPEAN LARCH from AUSTRIA, THE CZECH REPUBLIC & BAVARIA ⁶											
Tabulated design values are the minimum values for the following species and commercial grades in Table 4F: NORWAY SPRUCE from GERMANY, NE FRANCE, & SWITZERLAND; SCOTS PINE from GERMANY ⁵ ; DOUGLAS FIR/EUROPEAN LARCH from AUSTRIA, THE CZECH REPUBLIC & BAVARIA ⁶ ; SILVER FIR (<i>Abies alba</i>) from GERMANY, NE FRANCE, & SWITZERLAND	Select Structural	2" & wider	950	425	125	355	1100	1.5	0.55	0.42	PLIB
	No. 1		725	325	125	355	975	1.4	0.51		
	No. 2		700	325	125	355	950	1.1	0.40		
	No. 3	400	175	125	355	550	1	0.37			
	Stud	2" & wider	550	250	125	355	600	1	0.37		
	Construction	2" - 4" wide	800	375	125	355	1150	1.1	0.40		
	Standard		450	200	125	355	975	1	0.37		
	Utility		225	100	125	355	625	0.9	0.33		
N SPR/SCOTP(I)EST/FIN/GER/LIT/ROM/SW/UKR											
NORWAY SPRUCE & SCOTS PINE from ESTONIA, FINLAND, GERMANY ⁵ , LITHUANIA, ROMANIA, SWEDEN & UKRAINE											
Tabulated design values are the minimum values for the following species and commercial grades in Table 4F: NORWAY SPRUCE from ESTONIA, LATVIA, & LITHUANIA; NORWAY SPRUCE from FINLAND; NORWAY SPRUCE from GERMANY, NE FRANCE, & SWITZERLAND; NORWAY SPRUCE from SWEDEN; NORWAY SPRUCE from ROMANIA & UKRAINE; SCOTS PINE from ESTONIA, LATVIA, & LITHUANIA; SCOTS PINE from FINLAND; SCOTS PINE from GERMANY ⁵ ; SCOTS PINE from SWEDEN; SCOTS PINE from AUSTRIA & THE CZECH REPUBLIC, ROMANIA, & UKRAINE	Select Structural	2" & wider	1150	525	100	210	1150	1.5	0.55	0.38	TP
	No. 1		800	350	100	210	1000	1.4	0.51		
	No. 2		575	250	100	210	825	1.1	0.40		
	No. 3	325	150	100	210	475	1	0.37			
	Stud	2" & wider	450	200	100	210	525	1	0.37		
	Construction	2" - 4" wide	650	300	100	210	1050	1.1	0.40		
	Standard		375	175	100	210	850	1	0.37		
	Utility		175	75	100	210	550	0.9	0.33		

Table 4G

Reference Design Values for Multi-Species and Country Graded Visually Graded Dimension Lumber (2" - 4" thick)^{1,2,3}

(Tabulated design values are for normal load duration and dry service conditions. See NDS 4.3 for a comprehensive description of design value adjustment factors.)

USE WITH TABLE 4G ADJUSTMENT FACTORS

Multi-Species and Country Label	Commercial Grade	Size Classification	Design values in pounds per square inch (psi)							Specific Gravity ⁴ G	Grade Stamping Agency
			Bending	Tension parallel to grain	Shear parallel to grain	Compression perpendicular to grain	Compression parallel to grain	Modulus of Elasticity			
			F _b	F _t	F _v	F _{c⊥}	F _c	E	E _{min}		
NORWAY SPRUCE & SCOTS PINE from GERMANY⁵, ROMANIA, SWEDEN or UKRAINE											
NSPR/SCOTP()GER/ROM/SW/UKR											TP
Tabulated design values are the minimum values for the following species and commercial grades in Table 4F: NORWAY SPRUCE from GERMANY, NE FRANCE, & SWITZERLAND; NORWAY SPRUCE from SWEDEN; NORWAY SPRUCE from ROMANIA & UKRAINE; SCOTS PINE from GERMANY ⁵ ; SCOTS PINE from SWEDEN, SCOTS PINE from AUSTRIA & THE CZECH REPUBLIC, ROMANIA, & UKRAINE	Select Structural		1200	550	100	270	1200	1.5	0.55	0.38	
	No. 1	2" & wider	800	375	100	270	1000	1.4	0.51		
	No. 2		575	250	100	270	825	1.1	0.40		
	No. 3		325	150	100	270	475	1	0.37		
	Stud	2" & wider	450	200	100	270	525	1	0.37		
	Construction		650	300	100	270	1050	1.1	0.40		
	Standard	2" - 4" wide	375	175	100	270	850	1	0.37		
Utility		175	75	100	270	550	0.9	0.33			
NORWAY SPRUCE & SCOTS PINE from GERMANY⁵ or SWEDEN											
NSPR/SCOTP()GER/SW											TP
Tabulated design values are the minimum values for the following species and commercial grades in Table 4F: NORWAY SPRUCE from GERMANY, NE FRANCE, & SWITZERLAND; NORWAY SPRUCE from SWEDEN; SCOTS PINE from GERMANY ⁵ ; SCOTS PINE from SWEDEN	Select Structural		1200	550	120	285	1200	1.6	0.58	0.42	
	No. 1	2" & wider	800	375	120	285	1000	1.4	0.51		
	No. 2		575	250	120	285	825	1.1	0.40		
	No. 3		325	150	120	285	475	1	0.37		
	Stud	2" & wider	450	200	120	285	525	1	0.37		
	Construction		650	300	120	285	1050	1.1	0.40		
	Standard	2" - 4" wide	375	175	120	285	850	1	0.37		
Utility		175	75	120	285	550	0.9	0.33			
NORWAY SPRUCE & SCOTS PINE from SWEDEN											
NSPR/SCOTP()SW											TP
Tabulated design values are the minimum values for the following species and commercial grades in Table 4F: NORWAY SPRUCE from SWEDEN; SCOTS PINE from SWEDEN	Select Structural		1250	550	120	285	1200	1.6	0.58	0.42	
	No. 1	2" & wider	825	375	120	285	1000	1.4	0.51		
	No. 2		575	250	120	285	825	1.2	0.44		
	No. 3		325	150	120	285	475	1.1	0.40		
	Stud	2" & wider	450	200	120	285	525	1.1	0.40		
	Construction		650	300	120	285	1050	1.2	0.44		
	Standard	2" - 4" wide	375	175	120	285	850	1.1	0.40		
Utility		175	75	120	285	550	1	0.37			
NORWAY SPRUCE, SCOTS PINE & SILVER FIR from GERMANY⁵											
NSPR/SCOTP(SFIR()GER											TP
Tabulated design values are the minimum values for the following species and commercial grades in Table 4F: NORWAY SPRUCE from GERMANY, NE FRANCE, & SWITZERLAND; SCOTS PINE from GERMANY ⁵ ; SILVER FIR (<i>Abies alba</i>) from GERMANY, NE FRANCE, & SWITZERLAND	Select Structural		950	425	125	355	1100	1.5	0.55	0.42	
	No. 1	2" & wider	725	325	125	355	975	1.4	0.51		
	No. 2		700	325	125	355	950	1.1	0.40		
	No. 3		400	175	125	355	550	1	0.37		
	Stud	2" & wider	550	250	125	355	600	1	0.37		
	Construction		800	375	125	355	1150	1.1	0.40		
	Standard	2" - 4" wide	450	200	125	355	975	1	0.37		
Utility		225	100	125	355	625	0.9	0.33			

Table 4G

Reference Design Values for Multi-Species and Country Grademarked Visually Graded Dimension Lumber (2" - 4" thick)^{1,2,3}

(Tabulated design values are for normal load duration and dry service conditions. See NDS 4.3 for a comprehensive description of design value adjustment factors.)

USE WITH TABLE 4G ADJUSTMENT FACTORS

Multi-Species and Country Label	Commercial Grade	Size Classification	Design values in pounds per square inch (psi)							Specific Gravity ⁴ G	Grade Stamping Agency
			Bending	Tension parallel to grain	Shear parallel to grain	Compression perpendicular to grain	Compression parallel to grain	Modulus of Elasticity			
			F _b	F _t	F _v	F _{c⊥}	F _c	E	E _{min}		
PP-LP	PONDEROSA PINE & LODGEPOLE PINE from NORTH AMERICA										PLIB, WWPA
Tabulated design values are the minimum values for the following species and commercial grades in Table 4A: SPRUCE-PINE-FIR (SOUTH); WESTERN WOODS	Select Structural	2" & wider	900	400	135	335	1050	1.2	0.44	0.36	
	No. 1		675	300	135	335	950	1.1	0.40		
	No. 2		675	300	135	335	900	1	0.37		
	No. 3	375	175	135	335	525	0.9	0.33			
	Stud	2" & wider	525	225	135	335	575	0.9	0.33		
	Construction Standard	2" - 4" wide	775	350	135	335	1100	1	0.33		
	Utility	200	100	135	335	600	0.8	0.29			
R. PINE/NSPR(N)/SPF/SPF(S)	RED PINE, NORWAY SPRUCE (NORTH), SPRUCE-PINE-FIR, & SPRUCE-PINE-FIR(S) from NORTH AMERICA										TP
Tabulated design values are the minimum values for the following species and commercial grades in Table 4A: NORTHERN SPECIES; NORWAY SPRUCE (NORTH); SPRUCE-PINE-FIR; SPRUCE-PINE-FIR(S)	Select Structural	2" & wider	950	425	110	335	1100	1.1	0.40	0.35	
	No. 1		625	275	110	335	850	1.1	0.40		
	No. 2		625	275	110	335	850	1.1	0.40		
	No. 3	350	150	110	335	500	1	0.37			
	Stud	2" & wider	475	225	110	335	550	1	0.37		
	Construction Standard	2" - 4" wide	700	325	110	335	1050	1	0.37		
	Utility	400	175	110	335	875	0.9	0.33			
Sc P (I) EST FIN GER LTH SW	SCOTS PINE from ESTONIA, FINLAND, GERMANY, LITHUANIA, or SWEDEN										PLIB
Tabulated design values are the minimum values for the following species and commercial grades in Table 4F: SCOTS PINE from ESTONIA, LATVIA, & LITHUANIA; SCOTS PINE from FINLAND; SCOTS PINE from GERMANY; SCOTS PINE from SWEDEN	Select Structural	2" & wider	1150	525	120	210	1150	1.5	0.55	0.45	
	No. 1		800	350	120	210	1000	1.4	0.51		
	No. 2		575	250	120	210	825	1.1	0.40		
	No. 3	325	150	120	210	475	1	0.37			
	Stud	2" & wider	450	200	120	210	525	1	0.37		
	Construction Standard	2" - 4" wide	650	300	120	210	1050	1.1	0.40		
	Utility	375	175	120	210	850	1	0.37			
Sitka Sp/HF	SITKA SPRUCE & HEM-FIR from U.S.										PLIB
Tabulated design values are the minimum values for the following species and commercial grades in Table 4A: HEM-FIR; SPRUCE-PINE-FIR (SOUTH)	Select Structural	2" & wider	1300	575	135	335	1200	1.3	0.47	0.36	
	No. 1		875	400	135	335	1050	1.2	0.44		
	No. 2		775	350	135	335	1000	1.1	0.40		
	No. 3	450	200	135	335	575	1	0.37			
	Stud	2" & wider	600	275	135	335	625	1	0.37		
	Construction Standard	2" - 4" wide	875	400	135	335	1200	1	0.37		
	Utility	500	225	135	335	1000	0.9	0.33			

Table 4G

Reference Design Values for Multi-Species and Country Graded Visually Graded Dimension Lumber (2" - 4" thick)^{1,2,3}

(Tabulated design values are for normal load duration and dry service conditions. See NDS 4.3 for a comprehensive description of design value adjustment factors.)

USE WITH TABLE 4G ADJUSTMENT FACTORS

Multi-Species and Country Label	Commercial Grade	Size Classification	Design values in pounds per square inch (psi)							Specific Gravity ⁴ G	Grade Stamping Agency
			Bending	Tension parallel to grain	Shear parallel to grain	Compression perpendicular to grain	Compression parallel to grain	Modulus of Elasticity			
			F _b	F _t	F _v	F _{c⊥}	F _c	E	E _{min}		
SPF/SPF-S			SPRUCE-PINE-FIR & SPRUCE-PINE-FIR (SOUTH) from NORTH AMERICA								TP
SPF/SPF(S)			SPRUCE-PINE-FIR & SPRUCE-PINE-FIR (SOUTH) from NORTH AMERICA								PLIB
SPF ^S /SPF			SPRUCE-PINE-FIR & SPRUCE-PINE-FIR (SOUTH) from NORTH AMERICA								WWPA
SPF/SPF-s			SPRUCE-PINE-FIR & SPRUCE-PINE-FIR (SOUTH) from NORTH AMERICA								NLGA
S-P-F/SPFs			SPRUCE-PINE-FIR & SPRUCE-PINE-FIR (SOUTH) from NORTH AMERICA								NLGA
Tabulated design values are the minimum values for the following species and commercial grades in Table 4A: SPRUCE-PINE-FIR; SPRUCE-PINE-FIR (SOUTH)	Select Structural		1250	575	135	335	1200	1.3	0.47	0.36	
	No. 1	2" & wider	875	400	135	335	1050	1.2	0.44		
	No. 2		775	350	135	335	1000	1.1	0.40		
	No. 3		450	200	135	335	575	1	0.37		
	Stud	2" & wider	600	275	135	335	625	1	0.37		
	Construction		875	400	135	335	1200	1	0.37		
	Standard	2" - 4" wide	500	225	135	335	1000	0.9	0.33		
Utility		225	100	135	335	675	0.9	0.33			
SPF/SPF-S AS/NSPR/SCOTP/SFIR(I)AUS/EST/FIN/GER/LTH/SW			SPRUCE-PINE-FIR & SPRUCE-PINE-FIR (SOUTH) from NORTH AMERICA, AUSTRIAN SPRUCE from AUSTRIA, NORWAY SPRUCE from ESTONIA, FINLAND, GERMANY, LITHUANIA, or SWEDEN, SCOTS PINE from AUSTRIA, ESTONIA, FINLAND, GERMANY ⁵ , LITHUANIA, or SWEDEN, & SILVER FIR from GERMANY								TP
Tabulated design values are the minimum values for the following species and commercial grades in Table 4A & 4F: SPRUCE-PINE-FIR; SPRUCE-PINE-FIR (SOUTH); AUSTRIAN SPRUCE from AUSTRIA & THE CZECH REPUBLIC; NORWAY SPRUCE from ESTONIA, LATVIA, & LITHUANIA; NORWAY SPRUCE from FINLAND; NORWAY SPRUCE from GERMANY, NE FRANCE & SWITZERLAND; NORWAY SPRUCE from SWEDEN; SCOTS PINE from AUSTRIA & THE CZECH REPUBLIC, ROMANIA, & UKRAINE; SCOTS PINE from ESTONIA, LATVIA, & LITHUANIA; SCOTS PINE from FINLAND; SCOTS PINE from GERMANY; SCOTS PINE from SWEDEN; SILVER FIR (<i>Abies alba</i>) from GERMANY, NE FRANCE, & SWITZERLAND	Select Structural		950	425	120	210	1100	1.3	0.47	0.36	
	No. 1	2" & wider	725	325	120	210	975	1.2	0.44		
	No. 2		575	250	120	210	825	1.1	0.40		
	No. 3		325	150	120	210	475	1	0.37		
	Stud	2" & wider	450	200	120	210	525	1	0.37		
	Construction		650	300	120	210	1050	1	0.37		
	Standard	2" - 4" wide	375	175	120	210	850	0.9	0.33		
Utility		175	75	120	210	550	0.9	0.33			

Table 4G

Reference Design Values for Multi-Species and Country Grademarked Visually Graded Dimension Lumber (2" - 4" thick)^{1,2,3}

(Tabulated design values are for normal load duration and dry service conditions. See NDS 4.3 for a comprehensive description of design value adjustment factors.)

USE WITH TABLE 4G ADJUSTMENT FACTORS

Multi-Species and Country Label	Commercial Grade	Size Classification	Design values in pounds per square inch (psi)							Specific Gravity ⁴ G	Grade Stamping Agency
			Bending	Tension parallel to grain	Shear parallel to grain	Compression perpendicular to grain	Compression parallel to grain	Modulus of Elasticity			
			F _b	F _t	F _v	F _{c⊥}	F _c	E	E _{min}		
SPF/SPF-S AS/NSPR/SCOTP/SFIR()AUS/FIN/GER/SW											
SPRUCE-PINE-FIR & SPRUCE-PINE-FIR (SOUTH) from NORTH AMERICA, AUSTRIAN SPRUCE from AUSTRIA, NORWAY SPRUCE from FINLAND, GERMANY, LITHUANIA, or SWEDEN, SCOTS PINE from AUSTRIA, FINLAND, GERMANY ⁵ , LITHUANIA, or SWEDEN, & SILVER FIR from GERMANY											
Tabulated design values are the minimum values for the following species and commercial grades in Table 4A & 4F: SPRUCE-PINE-FIR; SPRUCE-PINE-FIR (SOUTH); AUSTRIAN SPRUCE from AUSTRIA & THE CZECH REPUBLIC; NORWAY SPRUCE from FINLAND; NORWAY SPRUCE from GERMANY, NE FRANCE & SWITZERLAND; NORWAY SPRUCE from SWEDEN; SCOTS PINE from AUSTRIA & THE CZECH REPUBLIC, ROMANIA, & UKRAINE; SCOTS PINE from GERMANY ⁵ ; SCOTS PINE from SWEDEN; SILVER FIR (<i>Abies alba</i>) from GERMANY, NE FRANCE, & SWITZERLAND	Select Structural	2" & wider	950	425	120	210	1100	1.3	0.47	0.36	
	No. 1		725	325	120	210	975	1.2	0.44		
	No. 2		575	250	120	210	825	1.1	0.40		
	No. 3	325	150	120	210	475	1	0.37			
	Stud	2" & wider	450	200	120	210	525	1	0.37		
	Construction	2" - 4" wide	650	300	120	210	1050	1	0.37		
	Standard		375	175	120	210	850	0.9	0.33		
Utility	175		75	120	210	550	0.9	0.33			
SPF/SPF-S AS/NSPR/SCOTP/SFIR()AUS/GER/ROM/SW/UKR											
SPRUCE-PINE-FIR & SPRUCE-PINE-FIR (SOUTH) from NORTH AMERICA, AUSTRIAN SPRUCE from AUSTRIA, NORWAY SPRUCE from GERMANY, ROMANIA, SWEDEN, or UKRAINE, SCOTS PINE from AUSTRIA, GERMANY ⁵ , ROMANIA, SWEDEN, or UKRAINE, or SILVER FIR from GERMANY											
Tabulated design values are the minimum values for the following species and commercial grades in Table 4A & 4F: SPRUCE-PINE-FIR; SPRUCE-PINE-FIR (SOUTH); AUSTRIAN SPRUCE from AUSTRIA & THE CZECH REPUBLIC; NORWAY SPRUCE from GERMANY, NE FRANCE & SWITZERLAND; NORWAY SPRUCE from ROMANIA & UKRAINE; NORWAY SPRUCE from SWEDEN; SCOTS PINE from AUSTRIA & THE CZECH REPUBLIC, ROMANIA, & UKRAINE; SCOTS PINE from GERMANY ⁵ ; SCOTS PINE from SWEDEN; SILVER FIR (<i>Abies alba</i>) from GERMANY, NE FRANCE, & SWITZERLAND	Select Structural	2" & wider	950	425	100	260	1100	1.3	0.47	0.36	
	No. 1		725	325	100	260	975	1.2	0.44		
	No. 2		575	250	100	260	825	1.1	0.40		
	No. 3	325	150	100	260	475	1	0.37			
	Stud	2" & wider	450	200	100	260	525	1	0.37		
	Construction	2" - 4" wide	650	300	100	260	1050	1	0.37		
	Standard		375	175	100	260	850	0.9	0.33		
Utility	175		75	100	260	550	0.9	0.33			

Table 4G

Reference Design Values for Multi-Species and Country Graded Visually Graded Dimension Lumber (2" - 4" thick)^{1,2,3}

(Tabulated design values are for normal load duration and dry service conditions. See NDS 4.3 for a comprehensive description of design value adjustment factors.)

USE WITH TABLE 4G ADJUSTMENT FACTORS

Multi-Species and Country Label	Commercial Grade	Size Classification	Design values in pounds per square inch (psi)							Specific Gravity ⁴ G	Grade Stamping Agency
			Bending	Tension parallel to grain	Shear parallel to grain	Compression perpendicular to grain	Compression parallel to grain	Modulus of Elasticity			
			F _b	F _t	F _v	F _{c⊥}	F _c	E	E _{min}		
SPF/SPF-S AS/NSPR/SCOTP/SFIR(I)AUS/EST/FIN/GER/LTH/ROM/SW/UKR											
SPRUCE-PINE-FIR & SPRUCE-PINE-FIR (SOUTH) from NORTH AMERICA, AUSTRIAN SPRUCE from AUSTRIA, NORWAY SPRUCE from ESTONIA, FINLAND, GERMANY, LITHUANIA, or SWEDEN, SCOTS PINE from AUSTRIA, ESTONIA, FINLAND, GERMANY ⁵ , LITHUANIA, or SWEDEN, & SILVER FIR from GERMANY											
Tabulated design values are the minimum values for the following species and commercial grades in Table 4A & 4F: SPRUCE-PINE-FIR; SPRUCE-PINE-FIR (SOUTH); AUSTRIAN SPRUCE from AUSTRIA & THE CZECH REPUBLIC; NORWAY SPRUCE from ESTONIA, LATVIA, & LITHUANIA; NORWAY SPRUCE from FINLAND; NORWAY SPRUCE from GERMANY, NE FRANCE & SWITZERLAND; NORWAY SPRUCE from ROMANIA & UKRAINE; NORWAY SPRUCE from SWEDEN; SCOTS PINE from AUSTRIA & THE CZECH REPUBLIC, ROMANIA, & UKRAINE; SCOTS PINE from ESTONIA, LATVIA, & LITHUANIA; SCOTS PINE from FINLAND; SCOTS PINE from GERMANY ⁵ ; SCOTS PINE from SWEDEN; SILVER FIR (<i>Abies alba</i>) from GERMANY, NE FRANCE, & SWITZERLAND	Select Structural	2" & wider	950	425	100	210	1100	1.3	0.47	0.36	TP
	No. 1		725	325	100	210	975	1.2	0.44		
	No. 2		575	250	100	210	825	1.1	0.40		
	No. 3		325	150	100	210	475	1	0.37		
	Stud	2" & wider	450	200	100	210	525	1	0.37		
	Construction	2" - 4" wide	650	300	100	210	1050	1	0.37		
	Standard		375	175	100	210	850	0.9	0.33		
	Utility		175	75	100	210	550	0.9	0.33		
S-P-F/ NSpr(N)											
SPF/NSpr(N)											
SPRUCE-PINE-FIR & NORWAY SPRUCE (NORTH) from CANADA											
SPRUCE-PINE-FIR & NORWAY SPRUCE (NORTH) from CANADA											
Tabulated design values are the minimum values for the following species and commercial grades in Table 4A: SPRUCE-PINE-FIR; NORWAY SPRUCE (NORTH)	Select Structural	2" & wider	950	600	135	410	1100	1.5	0.55	0.40	NLGA
	No. 1		650	425	135	410	900	1.3	0.47		
	No. 2		650	425	135	410	900	1.3	0.47		
	No. 3		375	250	135	410	525	1.2	0.44		
	Stud	2" & wider	500	325	135	410	575	1.2	0.44		
	Construction	2" - 4" wide	700	475	135	410	1100	1.2	0.44		
	Standard		400	275	135	410	925	1.1	0.40		
	Utility		175	125	135	410	600	1.1	0.40		
S-P-F/ SPFs/NSpr(N)											
SPRUCE-PINE-FIR & SPRUCE-PINE-FIR (S) From NORTH AMERICA, & NORWAY SPRUCE (NORTH) from NORTH AMERICA											
Tabulated desing values are the minimum values for the following species and commercial grades in Table 4A: SPRUCE-PINE-FIR; SPRUCE-PINE-FIR (S); NORWAY SPRUCE (NORTH)	Select Structural	2" & wider	950	575	135	335	1100	1.3	0.47	0.36	NLGA
	No. 1		650	400	135	335	900	1.2	0.44		
	No. 2		650	350	135	335	900	1.1	0.40		
	No. 3		375	200	135	335	525	1	0.37		
	Stud	2" & wider	500	275	135	335	575	1	0.37		
	Construction	2" - 4" wide	700	400	135	335	1100	1	0.37		
	Standard		400	225	135	335	925	0.9	0.33		
	Utility		175	100	135	335	600	0.9	0.33		

Table 4G

Reference Design Values for Multi-Species and Country Grademarked Visually Graded Dimension Lumber (2" - 4" thick)^{1,2,3}

(Tabulated design values are for normal load duration and dry service conditions. See NDS 4.3 for a comprehensive description of design value adjustment factors.)

USE WITH TABLE 4G ADJUSTMENT FACTORS

Multi-Species and Country Label	Commercial Grade	Size Classification	Design values in pounds per square inch (psi)							Specific Gravity ⁴ G	Grade Stamping Agency
			Bending	Tension parallel to grain	Shear parallel to grain	Compression perpendicular to grain	Compression parallel to grain	Modulus of Elasticity			
			F _b	F _t	F _v	F _{c⊥}	F _c	E	E _{min}		
SPRUCE-PINE-FIR & SPRUCE-PINE-FIR (SOUTH) from NORTH AMERICA, NORWAY SPRUCE, & SCOTS PINE from GERMANY ⁵											
SPF/SPF-S NSPR/SCOTP() ¹ GER											TP
Tabulated design values are the minimum values for the following species and commercial grades in Table 4A & 4F: SPRUCE-PINE-FIR; SPRUCE-PINE-FIR (SOUTH); NORWAY SPRUCE from GERMANY, NE FRANCE, & SWITZERLAND; SCOTS PINE from GERMANY ⁵	Select Structural	2" & wider	1200	550	135	335	1200	1.3	0.47	0.36	
	No. 1		800	375	135	335	1050	1.2	0.44		
	No. 2		700	325	135	335	950	1.1	0.40		
	No. 3	400	175	135	335	550	1	0.37			
	Stud	2" & wider	550	250	135	335	600	1	0.37		
	Construction	2" - 4" wide	800	375	135	335	1150	1	0.37		
	Standard		450	200	135	335	975	0.9	0.33		
Utility	225		100	135	335	625	0.9	0.33			
SPRUCE-PINE-FIR & SPRUCE-PINE-FIR (SOUTH) from NORTH AMERICA, NORWAY SPRUCE, SCOTS PINE from GERMANY ⁵ , ROMANIA, SWEDEN, & UKRAINE											
SPF/SPF-S NSPR/SCOTP() ¹ GER/ROM/SW/UKR											TP
Tabulated design values are the minimum values for the following species and commercial grades in Table 4A & 4F: SPRUCE-PINE-FIR; SPRUCE-PINE-FIR (SOUTH); NORWAY SPRUCE from GERMANY, NE FRANCE, & SWITZERLAND; NORWAY SPRUCE from ROMANIA & UKRAINE; NORWAY SPRUCE from SWEDEN; SCOTS PINE from AUSTRIA & THE CZECH REPUBLIC, ROMANIA, & UKRAINE; SCOTS PINE from GERMANY ⁵ ; SCOTS PINE from SWEDEN	Select Structural	2" & wider	1200	550	100	270	1200	1.3	0.47	0.36	
	No. 1		800	375	100	270	1000	1.2	0.44		
	No. 2		575	250	100	270	825	1.1	0.40		
	No. 3	325	150	100	270	475	1	0.37			
	Stud	2" & wider	450	200	100	270	525	1	0.37		
	Construction	2" - 4" wide	650	300	100	270	1050	1	0.37		
	Standard		375	175	100	270	850	0.9	0.33		
Utility	175		75	100	270	550	0.9	0.33			
SPRUCE-PINE-FIR, SPRUCE-PINE-FIR (SOUTH) from NORTH AMERICA, NORWAY SPRUCE, SCOTS PINE from GERMANY ⁵ & SWEDEN											
SPF/SPF-S NSPR/SCOTP() ¹ GER/SW											TP
Tabulated design values are the minimum values for the following species and commercial grades in Table 4A & 4F: SPRUCE-PINE-FIR; SPRUCE-PINE-FIR (SOUTH); NORWAY SPRUCE; SCOTS PINE from GERMANY ⁵ ; SCOTS PINE from SWEDEN	Select Structural	2" & wider	1200	550	120	285	1200	1.3	0.47	0.36	
	No. 1		800	375	120	285	1000	1.2	0.44		
	No. 2		575	250	120	285	825	1.1	0.40		
	No. 3	325	150	120	285	475	1	0.37			
	Stud	2" & wider	450	200	120	285	525	1	0.37		
	Construction	2" - 4" wide	650	300	120	285	1050	1	0.37		
	Standard		375	175	120	285	850	0.9	0.33		
Utility	175		75	120	285	550	0.9	0.33			

Table 4G

Reference Design Values for Multi-Species and Country Grademarked Visually Graded Dimension Lumber (2" - 4" thick)^{1,2,3}

(Tabulated design values are for normal load duration and dry service conditions. See NDS 4.3 for a comprehensive description of design value adjustment factors.)

USE WITH TABLE 4G ADJUSTMENT FACTORS

Multi-Species and Country Label	Commercial Grade	Size Classification	Design values in pounds per square inch (psi)							Specific Gravity ⁴ G	Grade Stamping Agency
			Bending	Tension parallel to grain	Shear parallel to grain	Compression perpendicular to grain	Compression parallel to grain	Modulus of Elasticity			
			F _b	F _t	F _v	F _{c⊥}	F _c	E	E _{min}		
SYP/WEST WOODS/NORTH SPECIES			SOUTHERN PINE, WESTERN WOODS, & NORTHERN SPECIES from NORTH AMERICA								TP
Tabulated design values are the minimum values for the following species and commercial grades in Table 4A & 4B: SOUTHERN PINE; WESTERN WOODS; NORTHERN SPECIES	Select Structural	2" & wider	900	400	110	335	1050	1.1	0.40	0.35	
	No. 1		625	275	110	335	850	1.1	0.40		
	No. 2		625	275	110	335	850	1	0.37		
	No. 3	350	150	110	335	500	0.9	0.33			
	Stud	2" & wider	475	225	110	335	550	0.9	0.33		
	Construction	2" - 4" wide	700	325	110	335	1050	1	0.33		
	Standard		400	175	110	335	875	0.9	0.29		
Utility	175		75	110	335	575	0.8	0.29			
WH-S Fir			WESTERN HEMLOCK & PACIFIC SILVER FIR from U.S.								PLIB
Tabulated design values are the minimum values for the following species and commercial grades in Table 4A: HEM-FIR	Select Structural	2" & wider	1400	925	150	405	1500	1.6	0.58	0.43	
	No. 1 & Btr		1100	725	150	405	1350	1.5	0.55		
	No. 1		975	625	150	405	1350	1.5	0.55		
	No. 2	850	525	150	405	1300	1.3	0.47			
	No. 3	500	300	150	405	725	1.2	0.44			
	Stud	2" & wider	675	400	150	405	800	1.2	0.44		
	Construction	2" - 4" wide	975	600	150	405	1550	1.3	0.47		
Standard	550		325	150	405	1300	1.2	0.44			
Utility	250		150	150	405	850	1.1	0.40			

Table 4G Footnotes

1. Reference design values are applicable to lumber that will be used under dry conditions such as in most covered structures. For 2" to 4" thick lumber the DRY dressed sizes shall be used (see Table 1A) regardless of the moisture content at the time of manufacture or use. In calculating design values, the natural gain in strength and stiffness that occurs as lumber dries has been taken into consideration as well as the reduction in size that occurs when unseasoned lumber shrinks. The gain in the load carrying capacity due to increased strength and stiffness resulting from drying more than offsets the design effect of size reductions due to shrinkage.
2. The ALSC Board of Review permits the use of combination stamps in certain instances, provided that the associated Reference Design Value elements for such combination-stamped lumber be assigned based on the lowest value among the combined species/regions. For the Species and/or Countries combinations listed, each of the individual Reference Design Value (RDV) elements from Tables 4A, 4B, and 4F (i.e. - F_b , F_t , F_v , F_c , F_c , E , E_{min} , and G) have been compared on its own merit for each species/regions listed on the stamp; the lowest value found and tabulated is the applicable value to be used for each Species and/or Countries, Region, and Agency category in the table. RDVs are only available for countries/regions that have completed ALSC Board of Review approved sampling and testing plans. Not all species group/grade/size combinations listed may be available at any given time.
3. The three entries on the black bar show in order: 1) The label stamped on the lumber; 2) The intended mix of species and countries; and 3) Agency stamping the lumber.
4. Specific gravity, G , based on weight and volume when oven-dry.
5. SCOTS PINE from GERMANY does not include states of Baden-Wuerttemberg and Saarland.
6. Reference design values for DOUGLAS FIR/EUROPEAN LARCH from AUSTRIA, THE CZECH REPUBLIC & BAVARIA are applicable only for 2x4 dimensional lumber and shall not be multiplied by the size factor adjustment.