

Changes to the 2015 National Design Specification (NDS) for Wood Construction

John "Buddy" Showalter, P.E., Bradford K. Douglas, P.E.,
and Michelle Kam-Biron, S.E., P.E.

Introduction

The 2015 Edition of the *National Design Specification® (NDS®) for Wood Construction* was recently published. The updated standard designated *ANSI/AWC NDS-2015* was approved as an ANSI American National Standard on September 30, 2014 (Figure 1). The *2015 NDS* was developed by the American Wood Council's (AWC) Wood Design Standards Committee and is referenced in the *2015 International Building Code (IBC)*.

Primary changes to the *2015 NDS* are listed here and major topics are subsequently covered in more detail:

- Incorporation of cross-laminated timber (CLT) in several chapters of the NDS, including a new product chapter specific to CLT
- Added terminology for laminated strand lumber and oriented strand lumber
- Clarification that withdrawal design values for lag screws excludes the length of the tapered tip
- Inclusion of char rates for CLT and structural composite lumber
- Relocation of reference to *Special Design Provisions for Wind and Seismic (SDPWS)*




Figure 1. The 2015 NDS is now available and is referenced in the 2015 IBC.

Cross-Laminated Timber

The primary change to the *2015 NDS* is incorporation of design provisions for CLT. To keep CLT with other product chapters (4-9), Chapter 10 is renamed Cross-Laminated Timber and each subsequent chapter is renumbered accordingly. The one-sentence reference to SDPWS in 2012 NDS Chapter 14 was moved to Section 1.1.1.4, which allows Chapters 15 and 16 to remain unchanged.

In NDS Chapter 3, a time dependent deformation (creep) factor for design of CLT was added. The factor of 2.0 is associated with use in dry service conditions and is consistent with the factor of 2.0 for wood structural panels used in dry service conditions. For column design, CLT is associated with a "c" factor equal to 0.9 for calculation of the column stability factor, C_p , consistent with glulam.

The new CLT Chapter 10 is consistent with other product chapters in the NDS (see Table 10.3.1) but most closely modeled after Chapter 9 for wood structural panels. The applicable product standard for CLT is *ANSI/APA PRG 320 Standard for Performance-Rated Cross-Laminated Timber*

		ASD only		ASD and LRFD				LRFD only		
		Load Duration Factor	Wet Service Factor	Temperature Factor	Beam Stability Factor	Column Stability Factor	Bearing Area Factor	Format Conversion Factor	Resistance Factor	Time Effect Factor
$F_b(S_{eff})' = F_b(S_{eff})$	X	C_D	C_M	C_t	C_L	-	-	2.54	0.85	λ
$F_t(A_{parallel})' = F_t(A_{parallel})$	X	C_D	C_M	C_t	-	-	-	2.70	0.80	λ
$F_v(t_v)' = F_v(t_v)$	X	C_D	C_M	C_t	-	-	-	2.88	0.75	λ
$F_s(Ib/Q)_{eff}' = F_s(Ib/Q)_{eff}$	X	-	C_M	C_t	-	-	-	2.88	0.75	-
$F_c(A_{parallel})' = F_c(A_{parallel})$	X	C_D	C_M	C_t	-	C_p	-	2.40	0.90	λ
$F_{c\perp}(A)' = F_{c\perp}(A)$	X	-	C_M	C_t	-	-	C_b	1.67	0.90	-
$(EI)_{app}' = (EI)_{app}$	X	-	C_M	C_t	-	-	-	-	-	-
$(EI)_{app-min}' = (EI)_{app-min}$	X	-	C_M	C_t	-	-	-	1.76	0.85	-

and applicable design values are to be obtained from manufacturer's literature or code evaluation report.


Connection provisions were revised to accommodate CLT in Chapter 12, Dowel-Type Fasteners. A new section applicable for lag screw withdrawal from CLT's narrow edge (top, bottom, left or right edge) was added. For lag screws loaded in withdrawal from the narrow edge, the end grain factor, $C_{eg} = 0.75$, is applicable regardless of actual grain orientation. While the C_{eg} factor is normally applied only to end grain applications in other wood products, application to all grain orientations in narrow edges of CLT is intended to conservatively account for the mix of end grain and side grain in the narrow edge of a CLT panel where the minimum edge distance requirements for lag screws cannot be maintained (as opposed to small diameter nails and wood screws).

New sections applicable for wood screw and nail withdrawal from end grain of CLT were added. The approach of not recognizing wood screw or nail withdrawal from end grain of CLT is consistent with existing provisions for wood screws and nails in end grain of other wood products. The $C_{eg}=0.0$ factor is added to clarify that there is no design strength associated with such applications.

New sections were added to address determination of dowel bearing strengths for fasteners installed in CLT. For fasteners installed in the panel face, dowel bearing strength is based on direction of loading with respect to the grain orientation of the CLT ply at the shear plane. Where the loading direction is parallel to the grain at the shear plane, a reduced bearing length approach is used to account for effect of reduced bearing strengths in perpendicular to grain orientations in adjacent layers. For fasteners installed in the narrow edge, dowel bearing strength perpendicular to grain, $F_{e\perp}$, is the applicable bearing strength where fastener diameter, $D \geq 1/4"$ and is intended to account for: 1) presence of end grain bearing in the connection and 2) end distance, edge distance, and spacing of fasteners that would not otherwise comply with NDS provisions for placement for $D \geq 1/4"$ if applied to individual laminations of a CLT panel. For example, if the CLT panel is comprised of three 1-1/2 inch thick laminations, the total thickness would be 4-1/2 inches. Meeting edge distance requirements for 1-1/2 inch laminations might not be possible. For fasteners with $D < 1/4"$, a single value of F_e is the applicable bearing strength.

Reduced bearing lengths are used to account for perpendicular grain orientations in crossing laminations where fasteners are installed in the panel face, penetrate multiple laminations, and are loaded parallel to the face grain.

Figure 12I End Distance, Edge Distance and Fastener Spacing Requirements in Narrow Edge of Cross-Laminated Timber



A new section, table, and figure (see Figure 12I) includes end distance, edge distance, and spacing requirements for fasteners in the narrow edge of CLT. Fastener placement provisions are based on CLT cross section dimensions as opposed to individual laminations within the CLT. End distance, edge distance, and spacing requirements for fasteners in the panel face of CLT should be designed in accordance with existing NDS requirements for these fasteners in other wood products.

A new section for lag screws loaded laterally in the narrow edge of CLT was added. For lag screws installed in the narrow edge of CLT and loaded laterally, in addition to use of $F_{e\perp}$ for dowel bearing strength, the connection design value must also be adjusted by the end grain factor, $C_{eg}=0.67$, regardless of whether the fastener is installed in end grain or side grain. The factor is normally applied to end grain applications only, but for CLT it is intended to conservatively account for the mix of end grain and side grain in the narrow edge and to address difficulties in meeting minimum edge distance requirements if applied to individual laminations of the CLT. For fasteners with $D < 1/4"$, $C_{eg}=0.67$ is applicable where the fastener is installed in end grain.

Chapter 13, Split Ring and Shear Plate Connectors, clarifies that provisions for design of these types of connections are not directly applicable to CLT. Possible considerations for their use, as part of an engineered design, would need to include requirements for end and edge distance, spacing, and effects of perpendicular crossing laminations.

Chapter 14, Timber Rivets, consistent with design of shear plate and split ring connectors in CLT, clarifies that provisions for design of timber rivet connections are not directly applicable to CLT.

Chapter 16, Fire Design of Wood Members, includes a char rate model for CLT based on observations from testing. Accordingly, a new effective char depth equation and table for CLT were added (see Table 16.2.1B).

Table 16.2.1B Effective Char Depths (for CLT with $\beta_n=1.5\text{in./hr.}$)

Required Fire Endurance (hr.)	Effective Char Depths, a_{char} (in.)								
	lamination thicknesses, h_{lam} (in.)								
	5/8	3/4	7/8	1	1-1/4	1-3/8	1-1/2	1-3/4	2
1-Hour	2.2	2.2	2.1	2.0	2.0	1.9	1.8	1.8	1.8
1½-Hour	3.4	3.2	3.1	3.0	2.9	2.8	2.8	2.8	2.6
2-Hour	4.4	4.3	4.1	4.0	3.9	3.8	3.6	3.6	3.6

Structural Composite Lumber

In Chapter 8 on Structural Composite Lumber, terminology was added for LSL (laminated strand lumber) and OSL (oriented strand lumber). Structural composite lumber products LSL and OSL are addressed in *ASTM D5456 Standard Specification for Evaluation of Structural Composite Lumber Products* but have not previously been defined within the NDS. Added product definitions for LSL and OSL are consistent with those in ASTM D5456.

Chapter 16, Fire Design of Wood Members, was also revised to address structural composite lumber products (PSL, LVL, and LSL).

Withdrawal Design Values for Lag Screws

Chapter 12, *Dowel-Type Fasteners*, clarifies that the withdrawal design value for a lag screw excludes the length of the tapered tip. The addition of “excluding the length of the tapered tip” is consistent with the Table 12.2A table heading which says the length of thread penetration “shall not include the length of the tapered tip.”

NDS Supplement

The *2015 NDS Supplement* incorporates new design values for southern pine. The American Lumber Standard Committee (ALSC) Board of Review approved changes to design values for all grades and all sizes of visually-graded Southern Pine and Mixed Southern Pine lumber with a recommended effective date of June 1, 2013. Additionally, new and revised grades of machine stress-rated lumber and machine evaluated lumber are also included in the *2015 NDS Supplement*.

More Details

A comprehensive table listing section by section changes to the *NDS* is available in an appendix to this paper.

Availability

The *2015 NDS* with *2015 NDS Supplement* is currently available in electronic format (PDF) only. Once the *NDS Commentary* and other support documents to be included in the *2015 Wood Design Package* (WDP) are updated, printed copies will be available for purchase. Once the *NDS Commentary* and other support documents are complete, those who purchased electronic versions of the *2015 NDS* and *2015 NDS Supplement* will receive those documents in electronic format at no additional charge. Check the AWC website (www.awc.org) for status updates on the *2015 WDP*.

Conclusion

The *2015 NDS* represents the state-of-the-art for design of wood members and connections. Reference to the *2015 NDS* in the *2015 IBC* will make it a required design standard in those jurisdictions adopting the latest building code. However, building officials have the option to accept designs prepared in accordance with newer reference standards even if the latest building code has not been adopted in their jurisdiction. *IBC* 104.11 for alternate materials and design provides the authority having jurisdiction with that flexibility.

Authors

John “Buddy” Showalter, P.E. is Vice President of Technology Transfer, Bradford K. Douglas, P.E. is Vice President of Engineering, and Michelle Kam-Biron, P.E., S.E. is Director of Education with the American Wood Council. Contact Mr. Showalter (bshowalter@awc.org) with questions.

APPENDIX: SUMMARY OF CHANGES – NDS 2015 Edition

Section	Description of Change
Chapter 1	<ol style="list-style-type: none"> 1. Add cross laminated timber (CLT) to Section 1.1.1.1 to coordinate with the inclusion of design provisions for CLT in the NDS. 2. Update reference to the SDPWS 2015 edition and relocate the one sentence reference to SDPWS from 2012 NDS Chapter 14 to Section 1.1.1.4. 3. Add notation specific to the design of CLT in Section 1.6.
Chapter 2	Add CLT to Sections 2.2 and 2.3 to coordinate with the inclusion of design provisions for CLT in the NDS.
Chapter 3	<ol style="list-style-type: none"> 1. In Section 3.5.2, add time dependent deformation (creep) factor for design of CLT. The factor of 2.0 is associated with use in dry service conditions and is consistent with the factor of 2.0 for wood structural panels used in dry service conditions. 2. In Section 3.7, associate CLT with c factor equal to 0.9, for calculation of column stability factor, C_p. The factor $c = 0.9$ for column design is consistent with glulam.
Chapter 8	In Section 8.1.2, add terminology for LSL (laminated strand lumber) and OSL (oriented strand lumber). Structural composite lumber products LSL and OSL are addressed in ASTM D5456 but have not previously been defined within the NDS. Added product definitions for LSL and OSL are consistent with those in ASTM D5456.
Chapters 10-14	Rename Chapter 10 Cross-Laminated Timber and renumber subsequent chapters through Chapter 14. To keep CLT with other product chapters (4-9), Chapter 10 is renamed and each subsequent chapter is renumbered accordingly. As noted earlier, the one-sentence reference to SDPWS in 2012 NDS Chapter 14 was moved to Section 1.1.1.4, which allows Chapter 15 to remain unchanged.
New Chapter 10	Add new provisions for CLT to Chapter 10. The new CLT chapter is consistent with other product chapters in the NDS but most closely modeled after Chapter 9 for wood structural panels. The applicable product standard for CLT is ANSI/APA PRG320 Standard for Performance-Rated Cross-Laminated Timber and applicable design values are to be obtained from manufacturer's literature or code evaluation report.
Chapter 11 Renamed	Chapter 11 is renamed Mechanical Connections. Add CLT to Section 11.1.1.1 to coordinate with inclusion of connection design provisions for CLT in the NDS.
Chapter 12 Renamed	<p>Chapter 12 is renamed Dowel-Type Fasteners.</p> <ol style="list-style-type: none"> 1. Add CLT to Section 12.1.1 to coordinate with inclusion of connection design provisions for CLT in the NDS. 2. Revise 12.2.1.2 to clarify that the withdrawal design value for a lag screw excludes the length of the tapered tip. The addition of "excluding the length of the tapered tip" is consistent with the Table 12.2A table heading which says the

Section	Description of Change
	<p>length of thread penetration “shall not include the length of the tapered tip”.</p> <ol style="list-style-type: none"> <li data-bbox="440 222 1437 506">3. Add new Section 12.2.1.5 applicable for lag screw withdrawal from CLT’s narrow edge (top, bottom, left or right edge). For lag screws loaded in withdrawal from the narrow edge, the end grain factor, $C_{eg} = 0.75$, is applicable regardless of grain orientation. While the factor is normally applied to end grain applications only, for CLT it is intended to conservatively account for the mix of end grain and side grain in the narrow edge of a CLT panel and laminations as thin as 5/8” in combination with the larger diameters associated with lag screws (as opposed to small diameter nails and screws). <li data-bbox="440 527 1437 737">4. Add new Section 12.2.2.4 and 12.2.3.6 applicable for wood screw and nail withdrawal from end grain of CLT, respectively. The approach of not recognizing wood screw or nail withdrawal from end grain of CLT is consistent with existing provisions for wood screws and nails in end grain of other wood products. The $C_{eg}=0.0$ factor is added to clarify that there is no design strength associated with such applications. <li data-bbox="440 758 1437 1251">5. Add new Sections 12.3.3.5 and 12.3.3.6 to address determination of dowel bearing strengths for fasteners installed in CLT. For fasteners installed in the panel face, dowel bearing strength is based on direction of loading with respect to the grain orientation of the CLT ply at the shear plane. Where the loading direction is parallel to the grain at the shear plane, a reduced bearing length approach is used to account for effect of orthogonal grain orientations in adjacent layers (see Section 12.3.5.2). For fasteners installed in the narrow edge, $F_{e-perpendicular}$ is the applicable bearing strength where $D \geq 1/4$” and is intended to account for: 1) presence of end grain bearing in the connection and 2) end distance, edge distance, and spacing of fasteners that would not otherwise comply with NDS provisions for placement for $D \geq 1/4$” if applied to individual laminations comprising part of the thickness of a CLT panel. For fasteners with $D < 1/4$”, a single value of F_e is the applicable bearing strength (see Table 12.3.3). <li data-bbox="440 1272 1437 1409">6. In Section 12.3.5.2, reduced bearing lengths are used to account for perpendicular grain orientations in crossing laminations where fasteners are installed in the panel face, penetrate multiple laminations, and are loaded parallel to the face grain. <li data-bbox="440 1430 1437 1640">7. New Section 12.5.1.4, Table 12.5.1G, and Figure 11I add end distance, edge distance, and spacing requirements for fasteners in CLT. Fastener placement provisions for CLT are based on CLT cross section dimensions as opposed to individual laminations within the CLT. Minimum requirements for end distance, edge distance, and spacing, are in addition to existing installation requirements for nails and screws where placement must be adequate to avoid splitting. <li data-bbox="440 1661 1437 1925">8. Add new Section 12.5.2.3 for lag screws loaded laterally in the narrow edge of CLT. For lag screws installed in the narrow edge of CLT and loaded laterally, in addition to use of $F_{e-perpendicular}$ for dowel bearing strength, the connection design value must also be adjusted by the end grain factor, $C_{eg}=0.67$, regardless of whether the fastener is installed in end grain or side grain. The factor is normally applied to end grain applications only, but, for CLT it is intended to conservatively account for the mix of end grain and side grain in the narrow edge, laminations as thin as 5/8” in combination with the larger

Section	Description of Change
	diameters of lag screws, and possible non-compliance with edge distance, end distance, and spacing of lag screws if applied to individual laminations of the CLT. For fasteners with $D < 1/4"$, $C_{eg} = 0.67$ is applicable where the fastener is installed in end grain (See 12.5.2.2).
Chapter 13 Renamed	<p>Chapter 13 is renamed Split Ring and Shear Plate Connectors.</p> <p>Add CLT to Section 13.1.1 to coordinate with inclusion of design provisions for CLT in the NDS. The proposed addition clarifies that provisions for design of shear plate and split ring connections are not directly applicable to CLT. Possible considerations for their use, as part of an engineered design, would need to include requirements for end and edge distance, spacing, and effects of perpendicular crossing laminations.</p>
Chapter 14 Renamed	<p>Chapter 14 is renamed Timber Rivets.</p> <p>Delete one sentence reference to SDPWS in 2012 NDS Chapter 14 and relocate to Section 1.1.1.4 of the NDS. As part of the reference update, the reference to SDPWS is relocated to a new Section 1.1.1.4 of the NDS and removes the current one sentence reference to SDPWS in 2012 NDS Chapter 14.</p> <p>Add CLT to Section 14.1.1 to coordinate with inclusion of design provisions for CLT in the NDS. Consistent with design of shear plate and split ring connectors in CLT, the proposed addition clarifies that provisions for design of timber rivet connections are not directly applicable to CLT.</p>
Chapter 16	<p>Revise Section 16.2.1 Char Rate to include a non-linear char rate for CLT based on observations from testing, effective char depth table for CLT (see Table 16.2.1B), and to address structural composite lumber products (PSL, LVL, and LSL).</p>
References	References have been updated to coordinate with updated references included in SDPWS 2015. As part of the reference update, the reference to SDPWS is moved into Chapter 1 of the NDS in order to eliminate the current one sentence reference to SDPWS in the 2012 NDS Chapter 14.