

February 2024

ADDENDUM

to the 2024 Edition of the Design Values for Wood Construction (a supplement to the National Design Specification® (NDS®) for Wood Construction)

(All electronic versions)

Modify Section 2.1 as follows:

2.1 List of Sawn Lumber Species Combinations

Species or Species Combination			Design Values Provided in Tables		
Red Alder		WWPA	4A		

Add the following species and commercial grades to Table 4A:

Table 4A Reference Design Values for Visually Graded Dimension Lumber (2" - 4" thick)^{1,2,3}

(All species except Southern Pine — see Table 4B) (Tabulated design values are for normal load duration and dry service conditions. See NDS 4.3 for a comprehensive description of design value adjustment factors.)

USE WITH TABLE 4A ADJUSTMENT FACTORS

Species and commercial grade clas		Design values in pounds per square inch (psi)								
	Size classification	Bending	Tension parallel to grain	Shear parallel to grain	Compression perpendicular to grain	Compression parallel to grain	Modulus of Elasticity		Specific Gravity ⁴	Grading Rules Agency
		F _b	F _t	F _v	F _{c⊥}	F _c	Е	E _{min}	G	
RED ALDER										
Select Structural	2" & wider	<u>1,100</u>	<u>650</u>	<u>140</u>	<u>395</u>	<u>1,050</u>	1,400,000	510,000		
<u>No. 1</u>		<u>800</u>	<u>475</u>	<u>140</u>	<u>395</u>	<u>825</u>	<u>1,300,000</u>	470,000		
No. 2		<u>775</u>	<u>450</u>	<u>140</u>	<u>395</u>	<u>650</u>	1,300,000	470,000		
No. 3		<u>450</u>	<u>250</u>	<u>140</u>	<u>395</u>	<u>375</u>	1,100,000	400,000	0.44	14/14/DA
Stud		<u>600</u>	350	<u>140</u>	<u>395</u>	<u>400</u>	1,100,000	400,000	0.41	<u>WWPA</u>
Construction	875 2" - 4" wide 450 225		<u>500</u>	<u>140</u>	<u>395</u>	<u>875</u>	1,200,000	440,000		
<u>Standard</u>		<u>450</u>	<u>275</u>	<u>140</u>	<u>395</u>	<u>675</u>	<u>1,100,000</u>	400,000		
Utility		<u>125</u>	<u>140</u>	<u>395</u>	<u>425</u>	<u>1,000,000</u>	370,000			